



Powered by



Xtreme Easy

VDW 840 Plus

The VDW 840 plus Xtreme Easy is a pre-mixed, 1-component resin paving joint compound suitable for concrete pavers, natural stone, and tile. The following are a few specific details about the product:

- Water-permeable
- Air-drying
- Self-compacting
- Can be applied in light rain
- Clean, stain-free surface
- Pressure washer friendly
- 1/8" joint width suitable for ceramic tile, 1/4" for concrete pavers
- For pedestrian traffic loads

Available Colors



Neutral



Stone Grey



Silver Grey



Basalt

Technical Data

Application Time

Approx. 45 minutes at 20°C | 68°F* application temp.
*Quick hardening at higher temperatures, and slow hardening at lower temperatures.

Application Temperature

2-26°C | 37-80°F (Do not lay onto frozen ground.)

Compressive Strength

16.0 N/mm / 2320 psi

Flexural Strength

8.0 N/mm / 1160 psi

Minimum Joint Requirements

1/8" joint width

Recommended min. 30 mm / 1.18" depth

Joint widths >1/2": depth must be at least twice the width

Dry Density

Set mortar density: 1.6 g/cm³

Water Permeability

approx. 0.075 gal/min/sq. ft. for a joint fraction of 5%

Storage Life

18 months if stored unopened in sealed and undamaged packaging. Must also be kept dry and frost-free. Do not store at temperatures above 20°C / 68°F



Bringing you quality joint solutions using innovative products, backed by old fashioned service.

Installation Instructions

For GFTK VDW 840 Plus Xtreme Easy

1. Construction Site Requirements

A stable, load-bearing structure, water-permeable sub-base, and the bedding layer - we recommend the GFTK Xtreme Trass Bedding Compound (VDW 480) - must all be correctly designed and installed for the anticipated traffic loads and in accordance with ASTM. The GFTK VDW 840 Xtreme Easy jointing compound is designed for the quick and easy grouting of concrete pavers, ceramic tile, and natural stone. The Xtreme Easy cannot be used to compensate for any settlement of the substructure. Movement joints must be installed as necessary to comply with the required structural design and any anticipated levels of movement. The GFTK VDW 840 Xtreme Easy jointing compound can be applied on damp / wet paving and even in light rain.

2. Preparation

Preparation / Pre-wetting: Clean the surface thoroughly of all dirt, cement residues, organic materials, or any other possible contaminants, including cleaning out all of the joints to the required depth. We recommend a pre-treatment with the GFTK Xtreme Stone Protect 3-in-1 (VDW 950) for any porous and/or sensitive paving surfaces - Please allow at least 24 hours after application prior to grouting. Thoroughly pre-wet the surface of the paving and mask adjacent surfaces that are not to be jointed.

Always use clean and fresh tap water!

3. Filling the Joints

Open your bucket of GFTK VDW 840 Plus Xtreme Easy jointing compound and cut open the vacuum-sealed packaging. Pour the GFTK VDW 840 Plus Xtreme Easy jointing compound directly onto the pre-wetted surface in small

piles. Add water to the material using a gentle water spray, and work the self-compacting material thoroughly into the joints using a rubber/foam squeegee and/or stiff broom. If the viscosity of the product diminishes, re-moisten by spraying lightly with water from a hose. The paved area must be kept constantly wet during application. We recommend working from the highest to the lowest points. All tools and shoes should be regularly cleaned with water.

4. Cleaning Off

Remove any excess GFTK VDW 840 Plus Xtreme Easy jointing compound residue from the area by spraying lightly with water from a hose. Avoid washing material out of the joints. Be careful to clean the paved surface towards areas not yet jointed and do not allow any water containing residues to pond, stand, or dry out on the completed areas. Finally remove any remaining fine residues with a damp coconut fiber brush – do not brush any residual dry material into any unfilled joints. Chamfers must be brushed free carefully, as performance cannot be guaranteed on these. Clean this brush in water frequently.

5. Important Information

Remain off the freshly applied areas and protect them from heavy rain for a period of min. 24 hours, or until the paving surface is no longer tacky. Then the areas can be walked over.

In general, a strength test should be carried out before final clearance of the area after 7 days. A very thin film of the resin binder may remain on rough surfaces or any surfaces that are not cleaned thoroughly. This film will disappear after a period of exposure to traffic and weathering.

The GFTK VDW 840 Plus Xtreme Easy is not recommended for use around swimming pools - we instead recommend our Xtreme Ceramic, Xtreme, or Xtreme Plus jointing compound.

For added ease of installation, consider the use of the SHS hydro broom. Installation does work with a standard broom and a garden hose.

6. Recommended Tools



HydroBroom



How To Guide

No direct legal liability can be assumed based on the data in this Product Information Sheet, or from any verbal advice unless this advice is expressly confirmed by us in writing. This Product Information Sheet replaces all previous versions. We reserve the right to make changes. Effective November 2022.